



VAPOR

GYPSUM PLASTERBOARD
DRYWALL CONSTRUCTION


Technical Specifications

Dimensional tolerances	Type	Vapor	
	Colour	White	
	Thickness:	±0,5 mm	
	Width:	+0/-4 mm	
Length:	+0/-5 mm	Reaction to fire	A2-s1,d0 (B) EN 520
		Thermal conductivity	W/(m. °C) 0.25 EN ISO 10456
Application	Density	kg/m ³	≥ 630
	Dimensions		
	Thickness	mm	12.5, 15
	Width	mm	1200
	Length	mm	Vários


Ceilings



Wall linings



Partitions



Approximate weight

Board Thickness 12.5 mm	kg/m ²	6.8
Board Thickness 15 mm	Kg/m ²	8.5

Breaking loads


EN 520

Board Thickness		12.5	15
Longitudinal	N	≥550	≥650
Transversal	N	≥210	≥250

Covering

In grey paper on the visible side and aluminium film on the back, in order to guarantee protection against surface humidity .

Sizes (mm)



Edge type

Tapered Edge – TE



To maintain the integrity of the GYPFORD VAPOR board performance the board must be protected from exposure to adverse conditions during storage and during application